

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 October 2003 (23.10.2003)

PCT

(10) International Publication Number
WO 03/087216 A1

- (51) International Patent Classification⁷: C08L 23/04, (74) Agents: KRIJGSMAN, Willem et al.; DSM Patents & Trademarks, P.O. Box 9, NL-6160 MA Geleen (NL).
23/16
- (21) International Application Number: PCT/NL03/00259 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 7 April 2003 (07.04.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 1020366 11 April 2002 (11.04.2002) NL (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): DSM IP ASSETS B.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).
- (72) Inventors; and (75) Inventors/Applicants (*for US only*): BRULS, Wilhelmus, Gerardus, Marie [NL/NL]; Graaf Wolterhoevenstraat 32, NL-6243 BE Geulle (NL). REPIN, Johannes, Fredericus [NL/NL]; Klingbeemden 177, NL-6441 KX Brunssum (NL). WIDDERSHOVEN, Christian [NL/NL]; Sint Joosterweg 16 A, NL-6102 GB Echt (NL).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 03/087216 A1

(54) Title: POLYMER COMPOSITION WITH IMPROVED TEMPERATURE RESISTANCE

(57) Abstract: Polymer composition, comprising as main components - a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group; - a reactive thermoplastic polymer with a second functional group which can react with the first; and - a base polymer, comprising at least 55 wt% of a single site catalyst polymerised polyolefin, wherein the proportion of the base polymer amounts to more than 50 wt%, preferably to at least 55 wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components, the proportion of the reactive thermoplastic polymer amounts to more than 50 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound and the quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer is between 0.05 and 1.0 mgeq/g, and a method for the preparation of such a composition.

ABSTRACT OF THE DISCLOSURE

Polymer composition, comprising as main components: a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group; a reactive thermoplastic polymer with a second functional group which can react with the first; and a base polymer, comprising at least 55 wt% of a single site catalyst polymerised polyolefin, wherein the proportion of the base polymer amounts to more than 50 wt%, preferably to at least 55 wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components, the proportion of the reactive thermoplastic polymer amounts to more than 50 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound and the quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer is between 0.05 and 1.0 mgeq/g, and a method for the preparation of such a composition.